

Revcon Incorporated Bulletin

10870 Kalama River Road, Fountain Valley, California 92708, (714) 960-3346

PAINT SPECIFICATIONS

1983

SHERWIN WILLIAMS Sunfire 421,
An Acrylic Urethane Enamel

PAINT CODES:

36-33702	Limestone	36-33701	Light Taupe Met
36-32323	Dark Brown	36-34442	Black
36-312416	Dark Blue Met	36-31231-G	Midnight Green
36-31244-G	Ice Blue Met	36-30774-G	Light Green

To prepare the coach for painting on the aluminum,
mix the following:

PPG Polyelutch Wash Primer 97-687 100%

PPG Polyelutch Wash Primer Thinner 97-731 150%

PPG Polyelutch Wash Primer Acid 1/2 pint to a
gallon

CAUTION: After Wash is mixed, the life is only 3 hours.

1978 & 1979
1978 & 1979 PAINT FORMULAS

These formulas are based on a Ditzler paint mixing scale.

REVCON LIMESTONE ACRYLIC ENAMEL

<u>Mixing Color #</u>	<u># of Parts (Scale Reading)</u>
DMR 400	1012
" 490	1038
" 486	1166
" 484	1188
" 476	1210
DXR 495	1290 (Drier)
DMR 499	Fill to top (Clear)

REVCON TRIM BROWN SEMI - GLOSS

<u>Mixing Color #</u>	<u># of Parts (Scale Reading)</u>
DMR 464	120
" 486	396
" 490	1820
" 400	1852
" 476	20000
DXR 495	2080 (Drier)
DMR 499	3000 (Clear)
DX 265	Fill to Top (Flatening Agent)



Revcon Incorporated
10870 Kalama River Road, Fountain Valley, California 92708 (714) 968-3348

1978 - 1979

REVCAN SILVER BULLET

DITZLER PAINT SCALE

SILVER POLY (TOP)

3 - 5 Gal. DAR 8967

MED. GRAY POLY (CENTER)

2 - 5 Gal. DAR 2967

SEMI GLOSS BLACK (LOWER)

8 - Gal. DAR 9000

*DAR refers to Delstar